Dkt: KSC-12139

Title: CORROSION PREVENTION OF COLD ROLLED STEEL USING WATER DISPERSIBLE LIGNOSULFONIC ACID DOPED POLYANILINE

IN THE CLAIMS

This listing of the claims will replace all prior versions, and listings, of claims in the application:

- 1. (Original) An article of manufacture comprising a metal substrate and a coating in contact with the metal substrate, wherein the coating comprises:
 - (1) linearly conjugated π -systems;
- (2) residues of sulfonated lignin or a sulfonated polyflavonoid or derivatives of sulfonated lignin or a sulfonated polyflavonoid; and
 - (3) a film-forming resin.
- 2. (Original) The article of claim 1 wherein the derivatives comprise one or more hydroxy, methoxy, ethoxy, hydroxymethyl, or 2-hydroxyethoxy substituents;
- 3. (Original) The article of claim 1 wherein the residues are of sulfonated lignin or a sulfonated polyflavonoid.
- 4. (Original) The article of claim 1 wherein the linearly conjugated π -systems comprise repeating monomer units of aniline, thiophene, pyrrole, or phenyl mercaptan, wherein the repeating monomer units of aniline, thiophene, pyrrole, or phenyl mercaptan are optionally ring-substituted with one or more staight or branched alkyl, alkoxy, or alkoxyalkyl groups.
- 5. (Original) The article of claim 1 wherein the linearly conjugated π -systems comprise polyanilines.
- 6. (Original) The article of claim 1 wherein the linearly conjugated π -systems comprise polypyrroles or polythiophenes.
- 7. (Original) The article of claim 1 wherein the linearly conjugated π -systems comprise repeating monomer units selected from the group consisting of aniline, o-ethylaniline, m-

Title: CORROSION PREVENTION OF COLD ROLLED STEEL USING WATER DISPERSIBLE LIGNOSULFONIC ACID DOPED POLYANILINE

ethylaniline, o-ethoxyaniline, m-butylaniline, m-hexylaniline, m-octylaniline, 4-bromoaniline, 2-bromoaniline, 3-bromoaniline, 3-acetamidoaniline, 4-acetamidoaniline, 5-chloro-2-methoxyaniline, 5-chloro-2-ethoxyaniline, 2,5-dimethylaniline, 2,3-dimethylaniline, 2,5-dibutylaniline, 2,5-dimethoxyaniline, tetrahydronaphthylamine, 2-cyanoaniline, 2-thiomethylaniline, 3-(n-butanesulfonic acid)aniline, 2,4-dimethoxyaniline, 4-mercaptoaniline, 4-methylthioaniline, 3-phenoxyaniline, 4-phenoxyaniline, thiophene, pyrrole, and thiophenol.

- 8. (Original) The article of claim 1 wherein the linearly conjugated π -systems are grafted to the residues.
- 9. (Original) The article of claim 1 wherein the film-forming resin is selected from the group consisting of polyurethanes, epoxies, neutral resins, acidic resins, acrylics, polyesters, glycidyl acrylates, polyamides, polyimides, polyaramids, polycarbonates, polymethyl methacrylates, poly(amide-imides), polyvinyl fluorides, urea-formaldehyde, phenol-formaldehyde, melamine-formaldehyde and combinations thereof.
- 10. (Original) The article of claim 1 wherein the film-forming resin comprises an acrylic resin and a melamine formaldehyde resin.
- 11. (Original) The article of claim 1 wherein the film-forming resin is a water-borne resin.
- 12. (Original) The article of claim 1 wherein the film-forming resin is an organic-solvent-borne resin.
- 13. (Original) The article of claim 1 wherein the coating composition is a high solids formulation.
- 14. (Original) The article of claim 1 wherein the coating composition is UV radiation curable.

Dkt: KSC-12139

Filing Date: 07/11/2001

Title: CORROSION PREVENTION OF COLD ROLLED STEEL USING WATER DISPERSIBLE LIGNOSULFONIC ACID DOPED POLYANILINE

- 15. (Original) The article of claim 1 wherein the coating composition is a powder coating formulation.
- 16. (Original) The article of claim 1 wherein the coating composition comprises sulfonated lignin.
- 17. (Original) The article of claim 1 wherein the coating composition comprises sulfonated lignin and the linearly conjugated π -systems comprise polyanilines.
- 18-54. (Cancelled)
- 55. (Original) A method of protecting a metallic substrate from corrosion comprising:
- (1) contacting the substrate with a coating composition comprising: (a) linearly conjugated π -systems, (b) residues of sulfonated lignin or a sulfonated polyflavonoid or derivatives of sulfonated lignin or a sulfonated polyflavonoid; and (c) a film-forming resin; and
 - (2) curing the coating composition to form a corrosion resistant coating on the substrate.
- 56. (Original) The method of claim 55 wherein the derivatives contain one or more hydroxy, methoxy, ethoxy, hydroxymethyl, or 2-hydroxyethoxy substituents.
- 57. (Original) The method of claim 55 wherein the residues are of sulfonated lignin or a sulfonated polyflavonoid.
- 58. (Original) The method of claim 55 further comprising preparing a surface of the metallic substrate for adhesion to the coating composition.
- 59. (Original) The method of claim 55 wherein the linearly conjugated π -systems comprise repeating monomer units of aniline, thiophene, pyrrole, or phenyl mercaptan, wherein the

Dkt: KSC-12139

Filing Date: 07/11/2001

Title: CORROSION PREVENTION OF COLD ROLLED STEEL USING WATER DISPERSIBLE LIGNOSULFONIC ACID DOPED

POLYANILINE

repeating monomer units of aniline, thiophene, pyrrole, or phenyl mercaptan are optionally ringsubstituted with one or more staight or branched alkyl, alkoxy, or alkoxyalkyl groups.

- 60. (Original) The method of claim 55 wherein the linearly conjugated π -systems comprise polyanilines.
- 61. (Original) The method of claim 55 wherein the linearly conjugated π -systems comprise polypyrroles or polythiophenes.
- 62. (Original) The method of claim 55 wherein the linearly conjugated π-systems comprise repeating monomer units selected from the group consisting of aniline, o-ethylaniline, m-ethylaniline, o-ethoxyaniline, m-butylaniline, m-hexylaniline, m-octylaniline, 4-bromoaniline, 2-bromoaniline, 3-bromoaniline, 3-acetamidoaniline, 4-acetamidoaniline, 5-chloro-2-methoxyaniline, 5-chloro-2-ethoxyaniline, 2,5-dimethylaniline, 2,3-dimethylaniline, 2,5-dibutylaniline, 2,5-dimethoxyaniline, tetrahydronaphthylamine, 2-cyanoaniline, 2-thiomethylaniline, 3-(n-butanesulfonic acid)aniline, 2,4-dimethoxyaniline, 4-mercaptoaniline, 4-methylthioaniline, 3-phenoxyaniline, 4-phenoxyaniline, thiophene, pyrrole, and thiophenol.
- 63. (Original) The method of claim 55 wherein the linearly conjugated π -systems are grafted to the residues.
- 64. (Original) The method of claim 55 wherein the coating composition comprises sulfonated lignin.
- 65. (Original) The method of claim 55 wherein the coating composition comprises sulfonated lignin and the linearly conjugated π -systems comprise polyanilines.
- 66. (Original) The method of claim 55 wherein the film-forming resin is selected from the group consisting of polyurethanes, epoxies, neutral resins, acidic resins, acrylics, polyesters,

Filing Date: 07/11/2001

Title: CORROSION PREVENTION OF COLD ROLLED STEEL USING WATER DISPERSIBLE LIGNOSULFONIC ACID DOPED

POLYANILINE

glycidyl acrylates, polyamides, polyimides, polyaramids, polycarbonates, polymethyl methacrylates, poly(amide-imides), polyvinyl fluorides, urea-formaldehyde, phenol-formaldehyde, melamine-formaldehyde and combinations thereof.

- 67. (Original) The method of claim 55 wherein the film-forming resin comprises an acrylic resin and a melamine formaldehyde resin.
- 68. (Original) The method of claim 55 wherein the film-forming resin is a water-borne resin.
- 69. (Original) The method of claim 55 wherein the film-forming resin is an organic-solvent-borne resin.
- 70. (Original) The method of claim 55 wherein the coating composition is a high solids formulation.
- 71. (Original) The method of claim 55 wherein the coating composition is UV radiation curable.
- 72. (Original) The method of claim 55 wherein the coating composition is a powder coating formulation.
- 73. (Original) The method of claim 55 wherein the coating composition is a water-based latex.